




FAG

HS7022-E-T-P4S-UL

High speed spindle bearing

High speed spindle bearing HS70...-E, adjusted, in pairs or sets, contact angle $\alpha = 25^\circ$, restricted tolerances

Informacje techniczne



Twoja aktualna wersja produktu

Contact angle	E	Contact angle 25°
Sealing	Without	Not sealed
Cage	T	Laminated fabric cage
Tolerance class	P4S	Tolerance class P4S, FAG standard better than P4 to ISO 492:2023
Arrangement bearing set	U	Single bearing
Preload class	L	Preload light

Main Dimensions & Performance Data

d	110 mm	Bore diameter
D	170 mm	Outside diameter
B	28 mm	Width
C _r	45.500 N	Basic dynamic load rating, radial
C _{0r}	35.500 N	Basic static load rating, radial
C _{ur}	3.200 N	Fatigue load limit, radial
n _G Grease	11.000 1/min	Limiting speed for grease lubrication
n _G Oil	16.000 1/min	Limiting speed for oil lubrication
n _G	16.000 1/min	Limiting speed
≈m	2,076 kg	Masa



Mounting dimensions

d _a	121 mm	Diameter shaft shoulder
d _a	h12	Diameter shaft shoulder clearance
D _a	159 mm	Shoulder diameter outer ring
D _a	H12	Shoulder diameter outer ring clearance
r _{a max}	2 mm	Maximum recess radius
r _{a1 max}	1 mm	Maximum recess radius
E _{tk min}	133,3 mm	Minimum diameter injection pitch
E _{tk max}	136,5 mm	Maximum diameter injection pitch
E _{tk1 min}	129,2 mm	Minimum diameter injection pitch
E _{tk1 max}	136,5 mm	Maximum diameter injection pitch
a	46,6 mm	Distance between the apexes of the pressure cones

Dimensions

r _{min}	2 mm	Minimum chamfer dimension
r _{1 min}	2 mm	Minimum chamfer dimension
α	25 °	Contact angle

Temperature range

T _{min}	-30 °C	Operating temperature min.
T _{max}	100 °C	Operating temperature max.



Additional information

F_{VL}	267 N	Preload force light
F_{VM}	802 N	Preload force medium
F_{VH}	1.604 N	Preload force heavy
K_{aEL}	770 N	Lift-off force light
K_{aEM}	2.352 N	Lift-off force medium
K_{aEH}	4.792 N	Lift-off force heavy
c_{aL}	193 N/ μ m	Axial rigidity light
c_{aM}	287 N/ μ m	Axial rigidity medium
c_{aH}	373 N/ μ m	Axial rigidity heavy

Właściwości

- 

Obciążenie promieniowe
- 

Obciążenie osiowe jednokierunkowe
- 

Smarowanie smarem
- 

Smarowanie olejem
- 

Bez uszczelnienia